

Technical Product Information



ADiNO® WB 1206.0

PVAc D2 Adhesive

Application

- General purpose bonding in the furniture and wood-working industry
- Assembly bonding of soft and hard woods
- Flat bonding requiring short setting time

Characteristics

- Very fast setting
- Tough elastic glue line
- Durability class D2 according to DIN EN 204
- Good mechanical processing characteristics

Technical Data

Basis	:	PVAc
Solid content	:	approx. 60%
pH	:	approx. 4.5
Viscosity	Brookfield	: approx. 14,000 mPa.s
Density	:	approx. 1.12 g/cm ³
Application quantity	:	100-160 g/m ²
Open time	:	approx. 1-3 minutes
Pressing time	flat bonding	: 2-3 minutes
	wood assembly	: 3-5 minutes

Instruction for Use

Apply glue evenly by spatula, roller or automatic glue spreader. It is recommended that ambient temperature should be above 10°C. Wood moisture content must not be higher than 10-12%. Surfaces must be free of dust and grease. Factors like temperature, humidity, substrate and application quantities influence open time and pressing time; elevated temperatures shorten the setting and open times. To determine accurate working parameters, self-tests are necessary. To avoid contamination of conveyors and pressplates, use separating agent. Clean equipment with water.

Packaging / Storage

20 kg pail, 200 kg drum, other packing sizes on request / shelf-life 6 months after production date.
Keep in a cool and dry place; avoid frost

All information based on internal tests and many years of practical experience.

The variety of materials used and different work conditions, which lie beyond our control, preclude any claims based on this data. We recommend performing sufficient test and pilot run that our technical service team gladly support.

January 2025, Adino GmbH. Email: info@adinoklebstoffe.de – www.adinoklebstoffe.de
Eysseneckstraße 4, 60322 Frankfurt/Main, Germany